

PRODUCT DATA SHEET

Sikafloor®-264 HC

2- PART EPOXY ROLLER AND SEAL COAT

DESCRIPTION

Sikafloor®-264 HC is a two part, coloured epoxy resin.

USES

Sikafloor®-264 HC may only be used by experienced professionals.

Sikafloor®-264 HC is used as:

- Roller coat for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- Seal coat for broadcast systems, such as multi-storey and underground car parks, maintenance hangars and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES

- Good chemical and mechanical resistance
- Easy application
- Liquid proof
- Gloss finish
- Slip resistant surface possible

APPROVALS / STANDARDS

- Particle emission certificate Sikafloor-264 HC CSM Statement of Qualification – ISO 14644-1, class 4– Report No. SI 0904-480 and GMP class A, Report No. SI 1008- 533.
- Outgassing emission certificate Sikafloor-264 HC: CSM Statement of Qualification – ISO 14644-8, class 6,5 - Report No. SI 0904-480.
- Good biological Resistance in accordance with ISO 846, CSM Report No. 1008-533
- Fire classification in accordance with EN 13501-1, Report-No. 2013-B-2119/01, MPA Dresden, Germany, June 2013.
- 2-part epoxy roller and seal coat according to EN 1504-2: 2004 and EN 13813:2002.
- According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 550 / 500 g/l (Limits 2007 / 2010) for the ready to use product.
- The maximum content of Sikafloor-264 is < 500 g/l VOC for the ready to use product

PRODUCT INFORMATION

Chemical Base	Epoxy
Packaging	20 kg set ready to mix units (Part A + B)
	Part A : 15.8 kg containers
	Part B : 4.2 kg containers

Appearance / Colour	Resin - part A :	coloured, liquid	
	Hardener - part B :	transparent, liquid	
	Available in a number of colour shades. Please consult our Technical Sales Engineer for further details. Under direct UV exposure (sun, lamp, skylight, etc.) there may be some discolouration and colour deviation, this has no influence on the function and performance of the coating.		
Shelf Life	24 months from the date of production		
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +18 °C and +30 °C.		
Density	Part A	~1.64 kg/L	(DIN EN ISO 2811-1)
	Part B	~1.00 kg/L	at +23 °C
	Mixed resin	~1.40 kg/L	
Solid content by weight	~100 %		

TECHNICAL INFORMATION

Shore D Hardness	~76 (7 days / +23°C)	(DIN 53 505)
Abrasion Resistance	41 mg (CS 10/1000/1000) (8 days / +23°C)	(DIN 53 109)
Compressive Strength	~53 N/mm ² (Resin filled 1 : 0.9 with F36) (28 days / +23 °C)	(EN196-1)
Tensile Strength in Flexure	~20 N/mm ² (Resin filled 1 : 0.9 with F36) (28 days / +23 °C)	(EN 196-1)
Tensile Adhesion Strength	>1.5 N/mm ² (failure in concrete)	(ISO 4624)
Chemical Resistance	Resistance to many chemicals. Contact Sika Technical Service Department for specific information.	
Thermal Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7 d	+80 °C
	Short-term max. 12 h	+100 °C
	Short-term moist/wet heat* up to +80 °C where exposure is only occasional (steam cleaning etc.).	

SYSTEM INFORMATION

Systems	Roller Coating:	
	Primer*:	1-2 x Sikafloor®-161 HC/-160 HC (optional)
	Top Coat:	2 x Sikafloor®-264 HC
	Textured Roller Coating:	
	Primer*:	1-2 x Sikafloor®-161 HC/-160 HC (optional)
	Top Coat:	1-2 x Sikafloor®-264 HC + Extender T
	Broadcast system ~4 mm:	
	Primer*:	1-2 x Sikafloor®-161 HC/-160 HC
	Wearing Coarse:	1 x Sikafloor®-264 HC + quartz sand (0.1 - 0.3 mm)
	Broadcasting:	Quartz sand (0.4 - 0.7 mm) broadcast to excess
	Top Coat:	1-2 x Sikafloor®-264 HC

*Note: In cases of limited exposure and normal absorbent concrete substrates priming with Sikafloor®-161 HC/160 HC is not necessary.

APPLICATION INFORMATION

Mixing Ratio	Part A : part B = 79 : 21 (by weight)			
Consumption	Roller Coating:			
	Coating System	Product	Consumption	
	Primer	1-2 x Sikafloor®-161 HC/-160 HC	1-2 x 0.35-0.55 kg/m ² for each layer	
	Top Coat	2 x Sikafloor®-264 HC	2 x 0.3 - 0.5 kg/m ² for each layer	
	Textured Roller Coating:			
	Coating System	Product	Consumption	
	Primer	1-2 x Sikafloor®-161 HC/-160 HC	1-2 x 0.35-0.55 kg/m ² for each layer	
	Top Coat	1-2 x Sikafloor®-264 HC + 1 % bw Extender T	1-2 x 0.5 - 0.8 kg/m ² for each layer	
	Broadcast System ~4 mm :			
	Coating System	Product	Consumption	
	Primer	1 x Sikafloor®-161 HC/-160 HC	1 x 0.35-0.5 kg/m ² for each layer	
	Wearing Course	1 pbw Sikafloor®-264 HC 1 pbw quartz sand (0.1 - 0.3 mm)	~4 kg/m ² (~2 kg/m ² binder + ~2 kg/m ² quartz sand)	
	Broadcasting	Quartz sand 0.4 -0.7 mm	~4-6 kg/m ²	
Top Coat	1-2 x Sikafloor®-264 HC	1-2 x 0.6 - 0.8 kg/m ² for each layer		
These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.				
Ambient Air Temperature	+10 °C min. / +30 °C max.			
Relative Air Humidity	80 % r.h. max.			
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish. Note: Low temperatures and high humidity conditions increase the probability of blooming.			
Substrate Temperature	+10 °C min. / +30 °C max.			
Substrate Moisture Content	< 4 % pbw moisture content. Test method: Sika®-Tramex meter, CM-measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).			
Pot Life	Temperature	Time		
	+10 °C	~50 min		
	+20 °C	~25 min		
	+30 °C	~15 min		
Curing Time	Before applying Sikafloor®-264 HC on Sikafloor®-161 HC/-160 HC allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	24 h	3 d	
	+20 °C	12 h	2 d	
	+30 °C	8 h	1 d	
	Before applying Sikafloor®-264 HC on Sikafloor®-264 HC allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	30 h	3 d	
	+20 °C	24 h	2 d	
	+30 °C	16 h	1 d	
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.			

Applied Product Ready for Use

Temperature	Foot traffic	Light traffic	Full cure
+10 °C	~72 h	~6 d	~10 d
+20 °C	~24 h	~4 d	~7 d
+30 °C	~18 h	~2 d	~5 d

Note: Times are approximate and will be affected by changing ambient conditions.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. If in doubt apply a test area first.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling can be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials.
- The concrete or screed substrate has to be primed or levelled in order to achieve an even surface.
- High spots must be removed by e.g. grinding.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

MIXING

Prior to mixing stir part A mechanically. When all of part B has been added to part A, continuously mix for 3 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimize air entrainment.

MIXING TOOLS

Sikafloor®-264 HC must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment. For the preparation of mortars use a forced action mixer of rotating pan, paddle or trough type. Free fall mixers should not be used.

APPLICATION

Prior to application, confirm substrate moisture content, relative air humidity and dew point. If > 4 % pbw moisture content, Sikafloor® EpoCem® may be applied as a T.M.B. (temporary moisture barrier) system.

Primer

Make sure that a continuous, pore free coat covers the substrate. If necessary, apply two priming coats. Apply Sikafloor®-161 HC/-160 HC by brush, roller or squeegee. Preferred application is by using a squeegee and then backrolling crosswise.

Levelling

Rough surfaces need to be levelled first. Therefore use e.g. Sikafloor®-161 HC levelling mortar (see PDS).

Coating

Sikafloor®-264 HC as coating, can be applied by short-piled roller (crosswise).

Seal Coat

Sealer coats can be applied by squeegee and then back-rolled (crosswise) with a short-piled roller.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

MAINTENANCE

CLEANING

To maintain the appearance of the floor after application, Sikafloor®-264 HC must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

LIMITATIONS

- Do not apply Sikafloor®-264 HC on substrates with rising moisture.
- Do not blind the primer.
- Freshly applied Sikafloor®-264 HC must be protected from damp, condensation and water for at least 24 hours.
- For areas with limited exposure and normally absorbent concrete substrates priming with Sikafloor®-161 HC/-160 HC is not necessary for roller or textured coating systems.
- For roller / textured coatings: Uneven substrates as well as inclusions of dirt cannot and should not be covered by thin sealer coats. Therefore both substrate and adjacent areas must always be prepared and cleaned thoroughly prior to application.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

- For exact colour matching, ensure the Sikafloor®-264 HC in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Philippines Inc.
 888 Marcos Alvarez Ave.,
 Talon V, Las Piñas City, Philippines 1747
 Tel. No.: +63 2 8806-2875
 Fax. No.: +63 2 8806-2883
 Website: phl.sika.com



Product Data Sheet
 Sikafloor®-264 HC
 July 2019, Version 01.01
 020811020020000164

Sikafloor-264HC-en-PH-(07-2019)-1-1.pdf

