

MasterBrace[®] 4000

Epoxy resin adhesive for MasterBrace Laminate system

DESCRIPTION

MasterBrace 4000 is the adhesive for the **MasterBrace Laminate system** and a filling compound for irregular surfaces.

The **MasterBrace Laminate system** is based on ready to use carbon fibre laminate strips that provide high tensile strength and are suitable for supplemental, externally bonded reinforcement of concrete, timber and masonry elements.

RECOMMENDED USES

MasterBrace 4000 is used as an adhesive for the **MasterBrace Laminates** to concrete, steel and wood.

FEATURES AND BENEFITS

- **Long pot-life** – allows installation of long laminates
- **Thixotropic with high adhesive strength** – self-supporting requiring no external propping and with minimal drips and runs
- **High cured bond strength** – creating true composite with substrate

PROPERTIES

(Typical physical properties)

| | |
|----------------------------------|------------------------------------|
| Compressive strength | >60 MPa |
| Flexural strength | >30 MPa |
| Bonding, ASTM D 4541 Concrete | >3.5 MPa (concrete failure) |
| Steel | >5 MPa |
| Electrical resistivity | 10 ¹⁴ Ω m |
| Composition | Two component epoxy based adhesive |
| Mix ratio | 3A : 2B by weight |
| Colour | Grey |
| Specific Gravity @ 23°C | 1.5 |
| Full Cure @ 23°C | 7 days |
| Pot Life @ | |
| - 23°C | 40 mins |
| - 40°C | 20 mins |
| Tack Free @ | |
| - 23°C | 5 hours |
| - 40°C | 2 hours |

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

APPLICATION

Surface Preparation

Remove oils, grease, dust or any other loose material from the surface that may impair adhesion. Application of external reinforcement should only take place if the substrate has an inherent tensile strength of at least 1.5 MPa.

The surfaces of elements that are still in good condition or restored with repair mortar should be roughened sufficiently with grit blasting or similar. Angle grind, grit blast, or needle gun repaired surfaces, to remove smooth, cement paste rich surface layers (laitance) and ensure aggregate is exposed and substrate surface has a sufficient profile. A surface profile of CSP 3-4 is desirable. With degraded substrates, the whole damaged layer should be removed by scarifying, hydro-demolition or similar and then structural restoration carried out with a suitable mortar eg.

MasterEmaco S 5400CI, MasterBrace 1446 or MasterBrace 4000 to ensure surfaces are within allowable levelness and flatness tolerances.

Mixing

Mechanically pre-mix Part A before adding all of Part B and mixing for two minutes or until a homogeneous mix is produced using a slow speed drill and mixing paddle.

Application

Ensure a maximum substrate humidity of 4% and substrate temperature is at least 3°C above dew point. If necessary, apply a levelling coat of **MasterBrace 4000** using a putty knife, to fill any bug holes or imperfections. Recheck surface tolerances.

Apply a layer of **MasterBrace P 3500** by roller or brush, and apply the **MasterBrace 4000** while the primer is still tacky. Maximum layer thickness of **MasterBrace 4000** for re-profiling is 20 mm.

Remove the peel ply protective coating from the laminate surface before application of the **MasterBrace 4000**. If after removal and before installation the laminate has been contaminated clean with a white cloth and non-greasy solvent (like methylated spirits) before applying the **MasterBrace 4000**.



We create chemistry

MasterBrace® 4000

Apply one layer of **MasterBrace 4000**, of 1-1.5 mm thick, to both substrate and laminate surfaces. Place the **MasterBrace Laminate** on the substrate surface and using a hard roller, exert a constant pressure by moving the tool both ways in the direction of the fibres to expel air.

Aim for a final layer thickness of 1-3 mm of **MasterBrace 4000**.

Clean up excess adhesive with non-greasy solvent prior to hardening.

For further information about application, please obtain a copy of the BASF "Application Guide for MasterBrace Laminates" from BASF office or website.

ESTIMATING DATA

A 5kg kit of **MasterBrace 4000** yields approximately 3.3 litres. This is sufficient for approximately 1m² of laminate or a 10-12 m length of 80 mm wide laminate.

| MasterBrace 4000 Wet Film Thickness | | | | |
|-------------------------------------|---------------------------------|----------------|-----------------------|------------------------------|
| L | Thickness in mm /m ² | m ³ | pails /m ³ | m ² /mm thickness |
| 3.3 | 3.3mm | (0.0033) | 303 | 3.3 m ² |

PACKAGING

5 kg kits.

SHELF LIFE

MasterBrace 4000 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from BASF office or website.

MasterBrace-4000 ANZ-V7-0417

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd
ABN 62008437867
Level 12
28 Freshwater Place
Southbank VIC 3006
Freecall: 1300 227 300
www.master-builders-solutions.basf.com.au

BASF New Zeland Ltd
Level 4, 4 Leonard Isitt Drive
Auckland Airport 2022
Auckland, New Zealand
Freecall: 0800 334 877
www.master-builders-solutions.basf.co.nz

BASF Emergency Advice:
1800 803 440 within Australia (24hr)
0800 944 955 within New Zealand